

„KORTEX® GT PP“ – TECHNICAL DATASHEET



Die geo-logische Kompetenz

THE WOVEN GEOTEXTILE MADE FROM 100% POLYPROPYLENE SLITT TAPES.

			KORTEX® GT PP 150/100	KORTEX® GT PP 200/100	KORTEX® GT PP 270/60	KORTEX® GT PP 320/50
MECHANICAL PROPERTIES						
Tensile Strength <i>(EN ISO 10 319)</i>	MD min. tolerance	kN/m kN/m	160 -10	220 -20	270 -10	350 -30
Tensile Strength <i>(EN ISO 10 319)</i>	CD min. tolerance	kN/m kN/m	110 -10	100 -5	65 -5	55 -5
Elongation at break <i>(EN ISO 10 319)</i>	MD min. tolerance	% %	18 ±2	12 ±2	12 ±2	12 ±2
Elongation at break <i>(EN ISO 10 319)</i>	CD min. tolerance	% %	10 ±2	12 ±2	13 ±2	8 ±2
Cone Drop Test <i>(EN ISO 918)</i>	Min. tolerance	mm mm	6 +2	7 +4	8 +4	7 +3
CBR Puncture Resistance <i>(EN ISO 12 236)</i>	Min. tolerance	kN kN	12 -3	12 -3	12 -3	12 -3
HYDRAULIC PROPERTIES						
Water permeability normal to plane, k_v without load <i>(EN ISO 11 058)</i>	Min. tolerance	m/s m/s	$5 \cdot 10^{-2}$ $-2 \cdot 10^{-2}$	$6 \cdot 10^{-2}$ $-2 \cdot 10^{-2}$	$7 \cdot 10^{-2}$ $-2 \cdot 10^{-2}$	$2 \cdot 10^{-2}$ $-1 \cdot 10^{-2}$
Characteristic Opening Size $O_{90,w}$ <i>(EN ISO 12 956)</i>	Min. tolerance	mm mm	0,50 ±0,15	0,70 ±0,21	0,70 ±0,21	0,20 ±0,06
FORMS OF SUPPLY						
Width	m	max. 4,5				
Length	m	100				

KORTEX® GT PP - PRODUCTS ARE CHEMICAL-, BIOLOGICAL- AND UV-RESISTANT
The manufacturing of these products has been found to conform to the Quality System Standard **UNI EN ISO 9002; 1994**

TENSILE STRENGTHS AT 2%, 3% AND 5% AVAILABLE ON REQUEST.

THE VALUES GIVEN ARE INDICATIVE AND CORRESPOND TO AVERAGE RESULTS OBTAINED IN OUR LABORATORIES AND INDEPENDENT TESTING INSTITUTES.
THE RIGHT IS RESERVED TO MAKE CHANGES WITHOUT NOTICE AT ANY TIME
(Ö / D / OCTOBER 2002)

GEOFELT G.m.b.H.
Rainerstraße 14
Tel. +43 (732) 60 98 60
Fax +43 (732) 60 98 608
A-4020 Linz / Austria

Office Germany
Platzhoffstraße 17
Tel. (0202) 3702026
Fax (0202) 3702027
D-42115 Wuppertal

INTERMEDIATE GRADES AVAILABLE ON REQUEST.